



**SHORE A POLYURETHANES**

"Dedicated to QUALITY, SERVICE, SAFETY, and INNOVATION"

**ST-1060 A/B  
HIGH TEAR STRENGTH  
60 SHORE A POLYURETHANE ELASTOMER**

**PRODUCT HIGHLIGHTS:**

ST-1060 A/B is a multi purpose elastomer that can perform many functions. Special product characteristics are:

- Does not contain MOCA, MDA, or MDI
- Easy to use
- Cures at room temperature to produce a strong, resilient elastomer
- Exudate and volatile free
- Maintains a dry, tack free surface after cure

**PHYSICAL PROPERTIES:**

Hardness, Shore A ASTM D2240 .....	60 ± 5
Density, (g/cc) ASTM D792 .....	1.05
Cubic Inches per Pound.....	26.3
Tensile Strength, (psi) ASTM D412.....	900
Modulus of Elasticity, (psi) ASTM D412:	
@ 100% Elongation .....	300
@ 200% Elongation .....	445
@ 300% Elongation .....	560
Elongation, (%) ASTM D412 .....	590
Tear Strength, (pli) ASTM D624.....	120
Shrinkage, (in/in) linear ASTM D2566 .....	0.006

**HANDLING PROPERTIES:**

Mix Ratio (by weight):	
Part A .....	100 parts by weight
Part B .....	55 parts by weight
Mix Ratio (by volume):	
Part A .....	100 parts by volume
Part B .....	58 parts by volume
Specific Gravity @ 77°F (25°C):	
Part A .....	1.08
Part B .....	1.02
Viscosity, (cps) @ 77°F (25°C) Brookfield:	
Part A .....	10,000
Part B .....	690
Mixed.....	4,750
Work Time, (100-gram mass) @ 77°F (25°C) .....	25 minutes
Gel Time .....	35 minutes
Demold Time @ 77°F (25°C).....	6 - 8 hours

**CURE SCHEDULE/HEAT CURING:**

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 160°F (71°C).

**MOLD PREPARATION AND RELEASING:**

When ST-1060 A/B is used to reproduce molds from plaster, wood or other porous substrates, we would first recommend that they be sealed. Release agents may then be applied over the sealed surface.

**NOTE:**

Prolonged direct exposure to sunlight can affect the surface of this product. Cover molds or other products when storing outdoors. **The cure will be inhibited if cast against a tin catalyzed silicone RTV.**

**STORAGE:**

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from date of shipment when properly stored at room temperature. Purge opened containers with dry nitrogen before re-sealing.

**PACKAGING:**

Gallon kits.....	8 lbs. A, 4.4 lbs. B
5-Gallon kits .....	40 lbs. A, 22 lbs. B
55-Gallon drum kits.....	450 lbs. A, 248 lbs. B

**SAFETY PRECAUTIONS:**

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction.

Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

**IF CONTACT OCCURS:**

**Skin:** Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.

**Eyes:** Immediately flush with water for at least 15 minutes. Call a physician.

**Ingestion:** If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

**Refer to the Material Safety Data Sheet before using this product.**