



TC-890 A/B

RIGID 80 SHORE D URETHANE CASTING SYSTEM

PRODUCT DESCRIPTION:

TC-890 A/B incorporates a non-mercury based catalyst system that produces a tough 80 shore D material with a 5-minute work time. This system can be used to hand pour electronic housing, models of all kinds, and point of purchase items. This system is also available in a 20-minute work time (TC-892), and a 12-minute work time (TC-891).

PRODUCT HIGHLIGHTS:

- ✓ Non-mercury
- ✓ Convenient mixing ratio: 1 to 1 parts by weight
- ✓ Low viscosity, flows easily
- ✓ Demold time: 1-2 hours at ambient temperature in a silicone rubber mold (1/8" thick section)

PHYSICAL PROPERTIES:

Hardness, Shore D ASTM D2240	80 ± 2
Density, (g/cc) ASTM D792	1.14
Cubic Inches per Pound	25
Color/Appearance.....	White/Opaque
Tensile Strength, (psi) ASTM D638.....	7,600
Tensile Modulus, (psi) ASTM D638.....	2.4 x 10 ⁵
Elongation, (%) ASTM D638.....	10
Flexural Strength, (psi) ASTM D790	10,000
Flexural Modulus, (psi) ASTM D790.....	2.5 x 10 ⁵
Shrinkage, (in/in) linear 12" x 1/2" x 1/2"	0.004
Izod Impact, notched (ft-lb/in) ASTM D256	0.7
Heat Deflection Temperature, ASTM D648:	
66 psi	195°F (91°C)
264 psi	177°F (81°C)

Note: Reported physical properties based on elevated temperature cured test specimens.

HANDLING PROPERTIES:

Mix Ratio (by weight):	
Part A	100 parts by weight
Part B	100 parts by weight
Mix Ratio (by volume):	
Part A	88 parts by volume
Part B	100 parts by volume
Specific Gravity:	
Part A	1.18
Part B	1.04

HANDLING PROPERTIES (continued):

Viscosity, (cps) @ 77°F (25°C) Brookfield:

Part A	325
Part B	830
Mixed	725

Color:

Part A	Yellow
Part B	White

Work Time, 100g mass @ 77°F (25°C)5 minutes
Gel Time7 minutes
Demold Time @ 77°F (25°C)..... 1-2 hours

CURE SCHEDULE/HEAT CURING:

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 180°F (82°C). Support of the part may be required to prevent part deformation during heat cure.

NOTE:

It is advisable whenever possible to evacuate entrapped air prior to casting this system. The use of a de-airing agent can speed up the process. BJB's AF-7 antifoam works best as the de-airing agent. In conjunction with these support products BJB offers pigments in a wide variety of colors and stainless steel mixers called "Jiffy Mixers." If help is required call BJB for assistance. For additional information on the use of this product, refer to BJB Guidelines for Handling Polyurethane Products.

STORAGE:

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from date of shipment when properly stored at room temperatures. Purge opened containers with dry nitrogen before re-sealing.

PACKAGING:

Gallon Kits	8 lbs. A, 8 lbs. B
5-Gallon Kits	40 lbs. A, 40 lbs. B
55-Gallon Drum Kits	400 lbs. A, 400 lbs. B

SAFETY PRECAUTIONS:

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

IF CONTACT OCCURS:

- Skin:** Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.
- Eyes:** Immediately flush with water for at least 15 minutes. Call a physician.
- Ingestion:** If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

Refer to the Material Safety Data Sheet before using this product.

NON-WARRANTY "Except for a warranty that materials substantially comply with the data presented in Manufacturer's latest bulletin describing the product (the basis for this substantial compliance is to be determined by the standard quality control tests generally performed by Manufacturer), all materials are sold "AS IS" and without any warranty express or implied as to merchantability, fitness for a particular purpose, patent, trademark or copyright infringement, or as to any other matter. In no event shall Manufacturer's liability for damages exceed Manufacturer's sale price of the particular quantity with respect to which damages are claimed."